

FACTORY FINISH

2000 GRIT LSS

3000 GRIT LSS

4000 GRIT LSS

5000 GRIT LSP

5500 GRIT LSP

The MOTIV Factory Finish is now rated with a final Laser Scan (LS) Grit target. Some of our finishing processes end with Sanding (S) and some end with a Polish(P). Therefore, you will see either LSS or LSP after the grit rating.

BALL SPINNER

500 / 1000 / 1500x2

500 / 1000 / 2000

**500 / 1000 / 2000 /
4000**

**500 / 1000 / 2000 /
POLISHx2**

**500 / 1000 / 2000 /
4000x2 / POLISH**

When finishing with the ball spinner, each step above is performed for 15 seconds on each section. Where you see "x2" the process is 30 seconds on each section.

RESURFACING MACHINE

500x2 / 1000x2

500 / 2000x2

500 / 2000x3

**500 / 1000 /
POLISHx2**

**500 / 1000 / 2000 /
4000 / POLISH**

When finishing with the ball resurfacing machine, each step above is performed for 30 seconds. Where you see "x2" the process is 60 seconds and "x3" is 90 seconds.